



TRIOCOR MASTIC 4500 Modified epoxy primer

DESCRIPTION: A two-pack high-build modified epoxy zinc phosphate primer.

TYPE AND RECOMMENDED USE: Multi-functional epoxy coating is suitable for the protection of steelwork, including industrial, oil&gas and infrastructure facilities exposed up to C5 as defined in ISO 12944. May be used at temperature up to + 120 °C. Not for immersion service.

PHYSICAL CONSTANTS:

Colour: Grey.

Volume solids: 70±5 %

Theoretical spreading rate: 0.107 ltr/m² - 75 microns DFT.

Film thicknesses:

Typical thicknesses

Film thicknesses	WFT, microns	DFT, microns
Minimum	107	75
Maximum	393	275

Drying times:

Drying times for 75 microns DFT								
Substrate temperature	0°C	5°C	10°C	15°C	20°C	25°C	30°C	35°C
To touch	9 hours	5 hours	2 ½ hours	1 ½ hours	1 ¼ hours	1 hours	55 minutes	¾ hours
To recoat:								
TRIOCOR MASTIC 4500	32 hours	16 hours	8 hours	5 hours	4 hours	3 hours	2 ½ hours	2 hours
TRIOCOR FINISH 5500	32 hours	16 hours	8 hours	5 hours	4 hours	3 hours	2 ½ hours	2 hours

Drying time is thickness dependent. These figures are given as a guide only. Factors such as air movement and humidity must also be considered.

SURFACE PREPARATION:

Apply only on a dry and clean surface with a temperature at least 3°C above the dew point. There are following surface preparation stages: remedy imperfections to P2 in accordance with ISO 8501-3; remove oil and grease (if necessary); remove salt if necessary; blast clean to Sa 2½ in accordance with GOST R ISO 8501-1-2014 with average surface profile in the range 50 - 75 microns, if maintenance clean damaged areas thoroughly to minimum P St 3; dust, blast abrasives shall be removed from the surface after blast cleaning such that the particle quantity and particle size do not exceed rating 2 of ISO 8502-3.

Technical Data Sheet



APPLICATION DETAILS:

Material preparation:	A two component material. Before mixing with the Additive stir the Base and the Additive separately. Mixing Ratio is given in product certificates of quality.		
Pot life:	2 ½ hours – 15 °C	1 ½ hours – 20 °C	1 hour – 35 °C
Application method:	Airless Spray / Manual application.		
Thinner:	TRIOSOLV 0002 (if necessary), up to 5 % by volume for airless spray. Contact your O3-Coatings representative for additional data.		
Nozzle size (recommended):	.013" -.019"		
Operation pressure (recommended):	Not less than 150 bar.		
Cleaning of tools:	Thinner TRIOSOLV 0002 (other solvents may be used in consultation with O3-Coatings).		
Application conditions:	Should be applied at temperatures above -10°C; Relative humidity: 90% maximum; (In confined spaces provide adequate ventilation during application and drying).		
RECOMMENDED SYSTEMS:			
Preceding coat:	TRIOCOR ZINC 1700. Contact your O3-Coatings representative for additional data.		
Subsequent coat:	TRIOCOR FINISH 5500. Contact your O3-Coatings representative for additional data.		
STORAGE:	24 months from date of manufacture. Store in dry, shaded conditions at temperature between 0°C and +30°C in hermetic original package away from UV rays and other sources of heat.		
ADDITIONAL NOTE:	Numerical values quoted for physical data may vary slightly from batch to batch.		
PACKAGE:	Set "Base – Additive" 20L.		
HEALTH AND SAFETY:	Refer to the Safety Data Sheet before use.		